

### REMARKS

This Preliminary Amendment cancels, without prejudice, claims 1 to 11 in the underlying PCT Application No. PCT/DE99/03942. This Preliminary Amendment further cancels, without prejudice, claims 1 to 7 in the annex to the International Preliminary Examination Report and adds new claims 8 to 14. The new claims, inter alia, conform the claims to U.S. Patent and Trademark Office rules and do not add any new matter to the application.

In accordance with 37 C.F.R. § 1.121(b)(3), the Substitute Specification (including the Abstract, but without the claims) contains no new matter. The amendments reflected in the Substitute Specification (including Abstract) are to conform the Specification and Abstract to U.S. Patent and Trademark Office rules or to correct informalities. As required by 37 C.F.R. §§ 1.121(b)(3)(iii) and 1.125(b)(2), a Marked Up Version of the Substitute Specification comparing the Specification of record and the Substitute Specification also accompanies this Preliminary Amendment. Approval and entry of the Substitute Specification (including Abstract) is respectfully requested.

The underlying PCT Application No. PCT/DE99/03942 includes an International Search Report, dated May 26, 2000, a copy of which is included. The Search Report includes a list of documents that were considered by the Examiner in the underlying PCT application.

The underlying PCT Application No. PCT/DE99/03942 also includes an International Preliminary Examination Report dated April 10, 2001, an English translation of the annexed pages thereto are enclosed herewith.

[illegible]

4

PROCESS FOR COATING HOLLOW BODIESFIELD OF THE INVENTION

The present invention relates to a process for coating hollow bodies, in which a powder mixture comprising a metal donor powder, an inert filler powder and an activator powder is provided, the powder mixture is brought into contact with an inner surface, which is to be coated, of the body, e.g., [comprising] including an Ni-, Co- or Fe-base alloy, and is heated.

BACKGROUND INFORMATION

[The known] Conventional processes for the diffusion coating of components made from heat-resistant alloys, such as Ni-, Co- or Fe-base alloys, include [what are known as the] so-called powder pack processes. A process of this type is [disclosed] described, for example in [US] U.S. Patent No. 3,667,985, in which the component surfaces to be coated are brought into contact with a donor powder [comprising] including titanium and aluminum, to which an inert filler material and a halide activator are admixed, and is heated. [US] U.S. Patent No. 3,958,047 [has disclosed] describes a powder pack process in which the metallic component is brought into contact with a donor powder which contains aluminum and chromium and is diffusion-coated by heating.

These processes are particularly suitable for coating the outer surfaces of metallic components, producing layer thicknesses of between 50 and 100  $\mu\text{m}$ . However, [the] these processes have inherent drawbacks when coating internal surfaces, and consequently the internal layer thicknesses which are achievable with relatively complicated geometrical forms with narrow gaps, tight angles or undercuts are limited and inadequate, generally being below 30  $\mu\text{m}$ . A problem in this

respect is that the donor powders have only a low ability to flow and therefore do not sufficiently fill the cavities. Moreover, after the coating, the donor powder can only be removed from the cavities with difficulty, and it is not possible to avoid leaving residues, and also the donor powder sinters to the surfaces.

The abovementioned drawbacks of the powder pack processes can in part be eliminated using [what are known as] so-called gas diffusion coating processes. One process of this type is [known from US] described in U.S. Patent No. 4,148,275, in which a powder mixture which contains, for example, aluminum is arranged in a first chamber and the metallic components to be coated are arranged in a second chamber of a vessel. The coating gas is generated by heating the powder and, using a carrier gas, is deposited on the outer and inner surfaces of the components to be coated. However, [the] these gas diffusion coating processes have the drawback that the devices for carrying out the process, such as, for example, for the forced guidance of the coating gases, are complex and expensive compared to those used for the powder pack processes. Furthermore, [in this case too,] the internal layer thicknesses which can be achieved are limited, since the coating gas or the donor metal gas is depleted on its route through the cavities of the component and a layer thickness gradient is produced along the length of the cavity. Since process conditions mean that the layer thickness of the outer coating is greater than that of the inner coating, the service life of the component is limited on account of the thinner internal coating.

[US] U.S. Patent No. 4,208,453 [has disclosed] describes a process for the diffusion coating of the inner and outer surfaces of components, such as gas turbine blades, in which a powder mixture comprises 10% of chromium donor powder with a particle size of from 10 to 20  $\mu\text{m}$  and 90% of alumina granules

with a particle size of from 100 to 300  $\mu\text{m}$ . In addition, a metal halide is added as activator. This [disclosure] process does not deal with measures for increasing the layer thickness in cavities of complicated geometry.

5

[DE] German Published Patent Application No. 30 33 074 [A1 discloses] describes a process for the diffusion coating of the inner surface of cavities, in which a metallic workpiece can be coated with an aluminizing diffusion powder mixture comprising 15% of aluminum powder with a particle size of 40  $\mu\text{m}$  and 85% of alumina powder with a particle size of approximately 200 to 300  $\mu\text{m}$ , as well as an  $\text{NH}_4\text{Cl}$  powder.

[US] U.S. Patent No. 5,208,071 [discloses] describes a process for aluminizing a ferritic component with an alumina slurry, followed by heat treatment, the slurry [comprising] including at least 10% by weight of chromium, at least 10% by weight of inert filler material, at least 12% by weight of water, a binder and a halogen activator, and finally the coated ferritic component is heat-treated. The process technology involved means that the use of a slurry differs significantly from a powder pack coating process.

[GB] British Published Patent Application No. 2 109 822 [A has disclosed] describes a metal diffusion process with which diffusion coatings can be produced more quickly than in the powder pack process, the coating powder being in loose form and being kept in contact with the component to be coated, in particular including with its internal surface, by mechanical means during the heating. The composition of the coating powder may comprise 10 to 60% of chromium powder, 0.1 to 20% of chromium halide and alumina.

[The problem on which] It is an object of the present invention [is based is that of improving a] to provide an

improved powder pack process [of the generic type described in the introduction in such a way] so that the layer thicknesses of the internal coating are sufficiently great even in the case of cavities with relatively complex geometries.

5

#### SUMMARY

According to one example embodiment of the present invention, [the solution to this problem is characterized in that] the inert filler powder [is provided with] has a mean particle size which is approximately the same as the mean particle size of the metal donor powder.

10

[The] One advantage of the method according to the present invention is that, when the particle sizes are selected in this way, it is possible to increase the specific density without agglomeration of the powder mixture, for example, [on account of] due to an excessively high metal donor powder content. It is also ensured that there is no premature depletion of the donor metal. A powder mixture of this type has [good] sufficient flow properties and, in tight corners, gains access to internal cavities which are to be coated. It is possible to coat hollow bodies, such as guide vanes and rotor blades of gas turbines made from heat-resistant Ni-, Co- or Fe-base alloys. Even in tight corners or recessed regions of the cavities, the layer thicknesses of the internal coating [lie] are in the range [from] of 50 to 110  $\mu\text{m}$ , therefore ensuring that the internal coating functions as an oxidation-resistant and corrosion-resistant layer.

20

25

[In a preferred configuration, the] The metal donor powder and the inert filler powder [are provided with] may have a mean particle size of greater than 40  $\mu\text{m}$ , so that it is possible to achieve [good] sufficient permeation of the coating gas through the bed of the powder mixture.

35

The powder mixture [is preferably provided with] may include a metal donor powder content of 10 to 25% by weight, in order to prevent agglomeration of the powder mixture and to ensure [good] sufficient permeation through the bed.

5

Furthermore, [it is expedient for] an alloy [with] having a donor metal content of 20 to 80% by weight [to] may be provided as the metal donor powder, so that a sufficiently [great] large layer thickness is ensured [on account of] due  
10 to the high donor metal content.

[It may be advantageous for a] A mixture of an alloy [with] having a donor metal content of 40 to 70% by weight and an alloy [with] having a donor metal content of 30 to 50% by weight [to] may be provided as the metal donor powder, so that the depletion of the metal donor in the two alloys takes place in steps, i.e., with a time delay.

The metal donor powder and the inert filler powder may be provided with a mean or average particle size of 150  $\mu\text{m}$ . A powder mixture of this type has [good] sufficient flow properties and fills the cavities having the internal surfaces to be coated [well on account of] due to an advantageous specific bulk density. In addition, there is [good] sufficient  
20 permeation of the coating gas through the bed of the powder mixture.

[Further configurations of the invention are described in the subclaims.]

30

#### DETAILED DESCRIPTION

The present invention is explained in more detail below with reference to specific examples.

In a first example, the hollow body is a hollow turbine guide vane of a gas turbine, which is provided with an oxidation-resistant and corrosion-resistant layer.

5 The cavity has a length of approximately 160 mm. Its inner surfaces are spaced apart at between 2 and 6 mm and converge at two opposite end sections. To coat the inner surfaces of the guide vanes, a powder mixture [comprising] including approximately 20% by weight of metal donor powder and approximately 80% by weight of inert filler powder is provided. AlCr is selected as the metal donor powder, and  $\text{Al}_2\text{O}_3$  is selected as the inert filler powder. The melting point of AlCr is at least approximately  $100^\circ\text{C}$  higher than the coating temperature of approximately  $800^\circ\text{C}$  -  $1200^\circ\text{C}$ , so that there is no diffusion bonding of the metal particles to one another or agglomeration.

An activator powder forms approximately 3% by weight, the powder selected being  $\text{AlF}_3$ , i.e., a halide compound. Another example of a suitable activator powder is  $\text{CrCl}_3$ . A compound of this type [has to] should have a low [vapour] vapor pressure at the coating temperature, so that it is retained throughout the entire coating process. Moreover, a halide compound of the donor metal, in this case aluminum, is used, in order to avoid agglomeration as a result of a chemical reaction of the halogen with the donor metal.

[The mean particle size of the inert filler powder is  $100\ \mu\text{m}$ , and is significantly greater than the particle size of the metal donor powder, which is  $60\ \mu\text{m}$ .] The aluminum content, i.e., the metal donor content, in the metal donor powder is 50% by weight.

The powder mixture which has been prepared in this [way] manner is introduced into the cavity of the guide vanes for the purpose of coating the internal surfaces. The subsequent



coating [takes place] is performed at 1080°C with a holding time of 6 h, while the external coating, i.e., the coating of the outer surfaces of the guide vane, [can take place] may be performed simultaneously in a single-stage process using a conventional powder pack process or alternatively by [means of] a gas diffusion coating process.

In the internal coating which is deposited in this [way] manner, the Al content in the layer is between 30 and 35% by weight.

In a second example, an inert filler powder ( $\text{Al}_2\text{O}_3$ ) [with] having a mean particle size of approximately 100  $\mu\text{m}$  is [once] again selected, forming approximately 80% by weight of the powder mixture. As activator powder,  $\text{AlF}_3$  forming approximately 3% by weight of a powder mixture is selected and admixed.

Unlike in [Example 1] the first example, the metal donor powder, which forms approximately 20% by weight of the powder mixture, [comprises] includes two fractions. The first fraction is an alloy [comprising] including AlCr, in which the aluminum content is 50% by weight. In the second fraction, the donor metal content, i.e., the aluminum content, is lower, being 30% by weight. This measure [can] may be used to optimize the coating process [in such a manner] so that [first of all] the fraction with the lower Al content is depleted, but the coating process is continued by the fraction with the higher Al content. In this [way] manner, it is possible to increase the ductility of the layers on the inner surfaces of the guide vane.

The Al content in the inner layers is 24 to 28% by weight. The inner layer thicknesses are between 65 and 105  $\mu\text{m}$  and are therefore significantly above the layer thicknesses which can be achieved with the conventional (powder pack) processes.

In a third example, the hollow body is a hollow turbine guide vane of a gas turbine, which is provided with an oxidation-resistant and corrosion-resistant layer by [means of] a powder pack coating process. The elongate cavity is approximately 180 mm long. The inner surfaces are spaced apart at between 2 and 6 mm and converge at two opposite, longitudinal-side end sections. To coat the inner surface of the guide vane, a powder mixture [comprising] including approximately 15% by weight of metal donor powder and just below 85% by weight of inert filler powder is provided. Depending on the particular application, the metal donor powder content may [lie] be in the range [from] of 10 to 25% by weight. The metal donor powder is AlCr, and the inert filler powder is Al<sub>2</sub>O<sub>3</sub>. The activator powder used is a halogen compound, such as AlF<sub>3</sub>, forming approximately 3% by weight. The activator powder is therefore a halide compound of the donor metal Al.

The mean particle size of the inert filler powder is approximately equal to the mean particle size of the metal donor powder, being 150  $\mu$ m. The proportion of the donor metal Al in the metal donor powder, which is an alloy, is 50% by weight. The specific density of a powder pack mixture is high not because of a high metal donor powder content, but rather because of the selected particle size distribution. With this bed of the powder pack mixture, there is sufficient permeation by the coating gases emanating from the halide compound.

To coat the inner surface of the turbine guide vane, the powder mixture which has been prepared in this [way] manner is introduced into its cavity. At the selected particle size distribution of the inert filler powder and of the metal donor powder, the bed has [good] sufficient flow properties and gains access even to the tight corners of the cavity. The subsequent coating [takes place] is performed at 1080°C for a holding time of 6 h. It may be [carried out] performed at the

same time as the external coating, i.e., the coating of the outer surface of the turbine guide vane, which may [take place] be performed using a conventional powder pack process or also using a gas diffusion coating process. Generally, the  
5 coating is [carried out] performed on a plurality of turbine guide vanes simultaneously.

The Al content in the internal coating which has been deposited in this [way] manner is between 30 and 35% by weight  
10 and consequently in a highly advantageous range, i.e., there is, for example, no embrittlement of the layer.

Even in tight corners or recessed regions of the cavities, the layer thicknesses are in the range [from] of 60 to 110  $\mu\text{m}$ ,  
15 thus ensuring that the internal coating function has protection against oxidation and corrosion.

[Abstract] ABSTRACT

A process for coating hollow bodies, in which a powder mixture [comprising] including a metal donor powder, an inert filler powder and an activator powder [comprising] including a metal halide is provided, the powder mixture is brought into contact with an inner surface, which is to be coated, of the hollow body and is heated, in which process, in order to increase the internal layer thicknesses, the inert filler powder is provided with a mean particle size which is approximately the same as the mean particle size of the metal donor powder.